



Ceramic Tile & Stone Over Liquid Urethane Waterproofing Membranes TDS 112

Liquid applied urethane waterproof membranes are soft rubbery materials that are usually applied in a minimum thickness of 60 mil (1/16") and may be as thick as 90-125 mil (1/10" – 1/8"). This material cures slowly and is relatively soft and tacky after placement.

However, in order to install ceramic tile it is necessary to have a strong firm surface and to be able to walk on the surface.

It is not possible to walk on the urethane membrane, because the surface remains tacky for some days or even weeks. In addition, the material is rubbery and will move under load. Therefore, ceramic tiles would not have sufficient support and consequently, under traffic and point loading or normal service requirements, could develop severe cracking of the joints and even cracked and broken tiles when installed by thin bed method directly on urethane waterproofing.

The ceramic industry recommends that a conventional thick mortar bed be placed over soft urethane waterproofing membranes and over soft built-up asphaltic waterproofing membranes.

Where full support for thin bed installations of ceramic or stone tile is required, LATICRETE® Hydro Ban™ or LATICRETE 9235 Waterproofing Membrane would be installed in lieu of a urethane waterproofing membrane. LATICRETE Hydro Ban or LATICRETE 9235 Waterproofing Membrane are latex based membranes which are thin, load-bearing and completely compatible with LATICRETE Latex Thin-Set Mortars.

Technical Data Sheets are subject to change without notice. For latest revision, check our website at www.laticrete.com
TDS 112.doc R 12 June 2009



LATICRETE INTERNATIONAL, INC. ▪ 1 LATICRETE Park North ▪ Bethany, CT 06524-3423 USA
800.243.4788 ▪ support@laticrete.com ▪ www.laticrete.com

©2009 LATICRETE INTERNATIONAL, INC. LATICRETE, LATAPOXY, SPECTRALOCK and the  logo are Registered Trademarks of LATICRETE International, Inc.