



LATICRETE® Finish Coats

TDS 115

LATICRETE WALL FINISH COATS

All stuccos, renders, paints and finishes consisting of LATICRETE® Latex Liquids and LATICRETE Grout powders provide strong, weatherproof and long-lasting exterior and interior finishes. These finishes can even be used in submerged installations (i.e. swimming pools, fountains, etc...)

The use of sanded colored grout as a finish coat render is generally recommended in applications 1/8" – 1/4" (3-6mm) thick. When greater thickness of render is needed to correct irregular walls or floors, use LATICRETE 3701 Fortified Mortar Bed, or, LATICRETE 226 Thick Bed Mortar mixed with LATICRETE 8510 Bonding Admix or LATICRETE 3701 Mortar Admix, to bring up the level of the render minus the thickness of the finish color coat.

LATICRETE 1500 Sanded Grout gauged with LATICRETE 8510 Bonding Admix makes an excellent render or plaster when used as a tank lining for water tanks or finishing swimming pools, reflective pools, fountains, and decorative pools.

MATERIALS FOR PLASTER/RENDER APPLICATIONS CAN BE:

- LATICRETE 4237 Latex Additive mixed with LATICRETE PermaColor™ Grout or LATICRETE 1500 Sanded Grout
- LATICRETE 8510 Bonding Admix diluted with water (1:1) and then mixed with LATICRETE 1500 Sanded Grout
- LATICRETE 3701 Mortar Admix mixed with LATICRETE 1500 Sanded Grout

NOTE: The above referenced LATICRETE Latex Liquids may be mixed with LATICRETE 1500 Sanded Grout or LATICRETE 1600 Unsanded Grout to a heavy, paint-like consistency and applied with short nap or long nap rollers to provide finished color coats on: Concrete Surfaces, Cement Block Units, Mortar Beds, Existing Render or Stucco, and Fiber Cement Panels

LATICRETE 4237 Latex Additive is recommended with colored grouts when applied as paint coatings by brush or spray on interior or exterior walls. LATICRETE 4237 Latex Additive provides longer open time and gives good, wet overlap for subsequent sections of the wall. The slower drying LATICRETE 4237 Latex Additive prevents developing a sharp line between freshly applied coating and areas that may have begun to dry.

SWIMMING POOL FINISH COATS

LATEX FINISHING PLASTER: LATICRETE® PermaColor™ Grout mixed with either LATICRETE 4237 Latex Additive or LATICRETE 8510 Bonding Admix can be applied as a finish plaster coating 1/8" (3 mm) thick over clean, sound, contaminant free cement plaster, cement block, concrete or gunite.

FILLER COATS: To fill uneven surfaces by brush or roller, as well as make plaster coatings up to 1/8" (3 mm) thick, use LATICRETE 1500 Sanded Grout mixed with LATICRETE 3701 Mortar Admix or LATICRETE 8510 Bonding Admix.

Technical Data Sheets are subject to change without notice. For latest revision, check our website at www.laticrete.com
TDS 115.doc R 10 January 2011



LATICRETE INTERNATIONAL, INC. ▪ 1 LATICRETE Park North ▪ Bethany, CT 06524-3423 USA
800.243.4788 ▪ support@laticrete.com ▪ www.laticrete.com

©2011 LATICRETE INTERNATIONAL, INC. LATICRETE, LATAPOXY, SPECTRALOCK and the  logo are Registered Trademarks of LATICRETE International, Inc.