



# LATICRETE<sup>®</sup> Rapid-Set Latex Products

## TDS 116

### LATICRETE<sup>®</sup> 4237 RS RAPID LATEX ADDITIVE\* WITH LATICRETE 211 POWDER (or 1:1 PC/Sand)

Install Tile at Temperature	Ready for Foot Traffic	Ready for Heavy Traffic
45° F (7° C)	12 hours	14 hours
50° F (10° C)	6 hours	10 hours
60° F (16° C)	5 hours	8 hours
70° F (21° C)	4 hours	6 hours
80° F (27° C)	3 hours	3-1/2 hours
90° F (32° C)	2 hours	2-1/2 hours
Open Time	50 minutes @ 70°F (21°C)	
Pot Life	80 minutes @ 70°F (21°C)	

### LATICRETE 101 RAPID LATEX ADMIX WITH LATICRETE 317

Install Tile at Temperature	Ready for Foot Traffic	Ready for Heavy Traffic
45° F (7° C)	16 hours	20 hours
50° F (10° C)	12 hours	16 hours
60° F (16° C)	8 hours	12 hours
70° F (21° C)	6 hours	10 hours
80° F (27° C)	5 hours	7 hours
90° F (32° C)	4 hours	6 hours
Open Time	15 minutes @ 70° F (21°C)	
Pot Life	1 hour @ 70°F (21°C)	

\* Product available outside of the United States only.

Technical Data Sheets are subject to change without notice. For latest revision, check our website at [www.laticrete.com](http://www.laticrete.com)  
TDS 116.doc R 26 February 2010



**LATICRETE INTERNATIONAL, INC.** ▪ 1 LATICRETE Park North ▪ Bethany, CT 06524-3423 USA  
800.243.4788 ▪ [support@laticrete.com](mailto:support@laticrete.com) ▪ [www.laticrete.com](http://www.laticrete.com)

©2010 LATICRETE INTERNATIONAL, INC. LATICRETE, LATAPOXY, SPECTRALOCK and the  logo are Registered Trademarks of LATICRETE International, Inc.